

THE CONTENTS OF THIS DRAWING ARE THE EXCLUSIVE PROPERTY OF THE TECHNICAL MATERIEL CORP. ITS UNAUTHORIZED USE OR REPRODUCTION IN WHOLE OR IN PART IS STRICTLY FORBIDDEN.		REQ. PART UNIT		USED ON		GL-126	
		MODEL		ASS'Y. NO.		DATE	
		TR-147				9-18-62	

ADD 2% BY WEIGHT OF BENZOIL PEROXIDE TO 8001 POLYLITE. THEN ADD 15% BY WEIGHT OF 1/32 MFCF MILLED FIBERS. MIX WELL UNTIL ALL OF FILLER IS IN SUSPENSION.

NOTE: PLACE POTTED UNIT IN OVEN AND BAKE AT 200°F. FOR 1½ HOURS.

REQ. ITEM	PART NO.	DESCRIPTION		SYMBOL
		THE TECHNICAL MATERIEL CORP. MAMARONECK, NEW YORK		
		COMPOUND, POTTING		
		BENZOIL PEROXIDE & 8001 POLYLITE		
		CHECKER	ENG. APP.	
		DRAFTS		
		CH. NO.		
		DATE		
DESCRIPTION		SCALE:		
UNLESS OTHERWISE SPECIFIED: DIMENSIONS ARE IN INCHES TOLERANCES ON FRAC. ± 1/64 DEC. ± .005 ANGLES ± 1/2°		MAXIMUM ALLOWABLE TOLERANCES HAVE BEEN DETERMINED AND ANY DEVIATIONS WILL BE CAUSE FOR REJECTION. REMOVE ALL BURRS AND SHARP EDGES		
		TYPE & TEMPER	HEATTREAT.SPEC.	
		DRAWN	CHECKED	FINAL APPROVAL
				GL-126
		FINISH & SPEC. NO.		
		ELEC. DES. APP. MECH. DES. APP.		