

DATE 9-18-52

SH. 1 OF 1

COMPILED BY  
R.F.B.

TMC SPECIFICATION NO. S-134

TITLE: Crossarm Treatment (Creosot )

JOB 141

APPROVED *[Signature]*

Ref: EEI Standard TD-90

**Treatment:**

Pressure treatment with final retention of 6 pounds per cubic foot.

**Preservative:**

No. 1 creosote, in accordance with Specification P-1 of the American Wood-Preservers' Association, except that the residue above 335 C. shall be less than 10%.

**Penetration:**

The preservative should penetrate all the sapwood. It shall penetrate longitudinally not less than one and one-half inches from pinholes, bolt holes and from the ends. The preservative shall not injure the wood. After treatment, crossarms shall be reasonably clean to the touch and should remain so.